



# Aurora

**Solar Heat Control Properties**

**Fabrics Installed Internally, Zero-Degree Profile Angle**

Aurora Average Openness 3%	Solar Optical Properties*				Interior Shading Coefficient w/			
	TS	RS	AS	TV	Single		Insulating	
					1/4CL	1/4HA	1CL	1HA
White	13	68	19	8	0.31	0.30		
White/Bone	11	58	31	8	0.37	0.32		
White/Grey	7	46	47	5	0.46	0.36		
Bone	11	52	37	6	0.41	0.35		
Charcoal	3	5	92	2	0.67	0.49		
Charcoal/Bronze	3	7	90	2	0.66	0.48		

Aurora Average Openness 5%	Solar Optical Properties*				Interior Shading Coefficient w/			
	TS	RS	AS	TV	Single		Insulating	
					1/4CL	1/4HA	1CL	1HA
White	16	67	17	11	0.33	0.32		
White/Bone	14	58	28	9	0.38	0.34		
Bone	14	51	35	11	0.43	0.37		
Bone/Beige	12	47	41	9	0.45	0.38		
Eggshell	16	66	18	11	0.34	0.32		
Charcoal	6	5	89	6	0.69	0.51		
Charcoal/Bronze	6	7	87	6	0.68	0.50		
Grey/Bone	10	39	51	8	0.49	0.40		
White/Grey	10	45	45	8	0.46	0.38		
Grey/Charcoal	6	12	82	6	0.69	0.52		

\* Performance evaluations

TS = Solar Transmittance

RS = Solar Reflectance

AS = Solar Absorptance

TV = Visual Transmittance

1/4 CL = 1/4" Clear Glass

1/4 HA = 1/4" Heat Absorbing Glass

1CL = 1" Clear Glass

1HA = 1" Heat Absorbing Glass